

Polyurethane sealant RANAL**Description:**

This product is designed for protecting welded areas and the joints of a car body and a chassis. It is a one-component, quickly drying product. It hardens by reacting with the moisture. Hardened coat is characterized by good elasticity and adhesion to the surface. It does not shrink or crack, it is resistant to mechanical vibrations. It is also resistant to water and atmospheric factors. It can be covered with any type of acryl lacquer. Do not expose to UV radiation.

It can be used on the following surfaces:

- Plain steel
- Lacquered surfaces
- Polyester laminates

Instruction for use:

Apply on cleaned, degreased and dry surface. To be applied with pneumatic or hand gun. Recommended temperature of application ranges between +5 and +35°C.

Drying time:

External drying of the coat in the temperature of 20°C is equal to about 55minutes. After about 1,5 hours the surface can be lacquered. Total hardening of 4 mm thick coat results after 24 hours.

Colour:

White, black and grey.

Tools cleaning:

Acryl thinner or nitro.

Storage:

To be stored in dry and cool place, away from the sources of light and heat. Avoid sun exposure. Storage time of the product in the original package in the temperature 20°C is equal to 8 months.

Health and safety recommendations:

Apply safety data sheet of the particular product.

Packaging:

Art.Nr	Capacity, ml:	Package, pieces:	Weight of the carton, kg
20411 (white)	310	12	4,80
20431 (grey)	310	12	4,80
20441 (black)	310	12	4,80

This information is based on careful, laboratory research and our long-standing experience. Strong market position does not absolve us from constant control of the quality of our products. However, we are not responsible for the final results after incorrect use of the product.

RANAL Sp. z o.o.